SPRAY-DECK SYSTEM DECORATIVE CEMENTIOUS COATING SYSTEM

DESCRIPTION

SPRAY DECK SYSTEM: SPRAY DECK is a specially formulated, two-component, textured overlay system designed as a cover-up for a variety of existing concrete and masonry surfaces. From residential to commercial and industrial applications on horizontal or vertical surfaces, Spray-Deck is the ideal cover-up for unsightly existing concrete and masonry. Spray-Deck's unique resin emulsion system is specifically designed for a variety of concrete and masonry substrates.

FEATURES

- Highly textured, Safety first non-slip decorative surface.
- May be integrally colored and clear sealed (see Texture-Crete Installation Guide)
- May be sealed with Increte's Stain Sealers (see Spray-Deck Installation Guide)
- May be used on vertical or horizontal surfaces
- Extremely tough, durable, wear-bearing surface
- Stain resistant, easy to clean surface
- Flexibility of application allows for a multitude of effects

TECHNICAL INFORMATION

Impact Strength

Test Procedure: A one pound steel ball with a diameter of 1.9" was dropped from a height of six feet onto the mortared surface. Test Results: An indentation with a diameter of 0.45" was visible, however, no sign of cracking was present.

Tensile Strength

Tensile Strength at 1, 3, 7, and 28 days. Test: ASTM C-190. Results (in psi):

1 day	230
3 days	470
7 days	890
28 days	890

Compressive Strength

 Compressive strength at 1,3,7, and 28

 Days. Test: ASTM C-109. Results (in psi):

 1 day
 3,900

 3 days
 6,100

 7 days
 7,010

 28 days
 7,880

Flexural Strength

Test Procedure: Samples were wrapped around a 3' diameter cylinder with mortar side in tension. Test Results: No visible signs of cracking were observed.

Thermal Expansion & Contraction

At 8,9,12, and 14 Days. Test: ASTM C-531. Final Result: 0.10% shrinkage, $9.09 \times 10^{-6}in^{20}F$ Weight: 1 lb/ft², thickness: 0.125 in. **Thermal Conductivity** Test: ASTM C518-76 using 6.0 mm thickness specimen, 96.8 lb.ft., 75°F. Results: Apparent Thermal Conductivity 0.290 W/h.K, 2.01 BTU in 1hr/ft²⁰F. **Thermal Resistance** 0.12 BTU-1hr/ft²⁰F.



INCRETE SYSTEMS

1611 Gunn Hwy. Odessa, FL 33556 Phone: 813-886-8811 - Toll-Free: 800-752-4626 - Fax: 813-920-1516 www.increte.com

A Division of The Euclid Chemical Company An RPD Comp

SPRAY-DECK SYSTEM

DECORATIVE CEMENTIOUS COATING SYSTEM

PACKAGING

SPRAY DECK GROUT 50 lb. Bag SPRAY DECK RESIN 1 gal or 5 gal units CONCRETE STAIN SEALERS 1 gal or 5 gal units

SHELF LIFE

SPRAY DECK GROUT: 2 years in original unopened bag SPRAY DECK RESIN: 2 years in original unopened containers CONCRETE STAIN SEALERS: WATER BASED 2 years; SOLVENT BASED 3 years in original, unopened containers

COVERAGE

1 bag of SPRAY-DECK GROUT should cover 75 square ft. for a skim coat. 150 sq. ft. for a texture coat.

DIRECTIONS FOR USE

APPLICATION PROCESS

Preparation: Remove any loose material such as paint or chipped concrete. Degrease surface with Increte Systems GREASE-AWAY degreaser using 4-8 fl. Oz. of degreaser to one gallon of water. Acid wash surface with a 1 to 5 solution of muriatic acid in water.

Mixing:

1) Pre-mix SPRAY DECK RESIN 1 to 1 with cool, clean potable water

- 2) Add 4-6 quarts of pre-mixed resin and water to a clean 5-gallon plastic pail.
- 3) Slowly mix while adding 1-50 lb. Bag of SPRAY DECK GROUT.
- 4) Mix 2-3 minutes.

Application: Grout mixture can then be trowelled, squeegeed, or sprayed on to the surface not to exceed ¼" in thickness.

Seal: After at least 24 hours drying time, the surface must be scrapped, broomed, and blown with a high velocity blower and then sealed with Increte Systems Clear Seal or Increte Systems Concrete Stain Sealer.

MAINTENANCE

Clean surface as necessary with a soap/detergent and rinse with water.

PRECAUTIONS/LIMITATIONS

Avoid prolonged contact with skin, and avoid splashing in eyes. Flush affected areas thoroughly with water to remove.

WARRANTY All recommendations, statements and technical data contained herein based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his use of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person having any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations or statements other than those contained in written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

IMPORTANT NOTICE: THESE PRODUCTS ARE SOLD SUBJECT ONLY TO THE EXPRESSED WARRANTIES CONTAINED HEREIN. ADDITIONAL WARRANTIES, EXPRESSED OR IMPLIED, AND ANY WARRANTY OF MERCHANT ABILITY IS HEREBY EXCLUDED. BUYER AGREES THAT SELLER ASSUMES NO LIABILITY FOR CONSEQUENTIAL DAMAGES OF ANY KIND, WHICH RESULT FROM THE USE OR MISUSE OF THE MERCHANDISE SOLD HEREUNDER. IN THE EVENT THAT THE BUYER PROVES THAT ANY GOODS RECEIVED DO NOT CONFORM TO THE SPECIFICATIONS AGREED TO BETWEEN THE PARTIES OR IF THE BUYER PROVES THAT SUCH GOODS WERE DEFECTIVELY MANUFACTURED. THE BUYER'S REMEDIES SHALL BE LIMITED TO EITHER THE RETURN OF THE GOODS AND REFAYMENT OF THE PURCHASE PRICE OR REPLACEMENT OF THE NON-CONFORMING GOODS AT THE OPTION OF THE SELLER. SUCH REMEDY BEING EXCLUSIVE OF ALL OTHERS AND THE SOLE REMEDY AVAILABLE TO THE BUYER, HEREY EXPRESSLY WAIVES ANY CLAIM TO ADDITIONAL DAMAGES.